## B. In the Claims:

1. (Currently Amended) A positive electrode active material containing a lithium transition metal composite oxide represented by the general formula  $\text{LiCo}_x A_y B_z O_2$  where A denotes at least one element selected from the group consisting of Al, Cr, V, Mn and Fe, and B denotes at least one element selected from the group consisting of Mg and Ca and x, y and z are such that  $0.9 \le x < 1,0.001 \le y < 0.05$ , and  $0.001 \le z < 0.05$ ; and

wherein a band-shaped positive electrode comprising a metal foil is coated with a

positive electrode mixture containing the positive electrode active material and a binder, the

metal foil being coated by the mixture on both surfaces of the metal foil; and the positive

electrode being spirally wound with a negative electrode by interposing a separator in-between.

- 2. (Currently Amended) A non-aqueous electrolyte secondary cell comprising:
  - (a) a positive electrode,
  - (b) a negative electrode, and
- (c) a non-aqueous electrolyte interposed between said the positive and negative electrodes, said the positive electrode using having a positive electrode active material containing a lithium transition metal composite oxide represented by the general formula  $\text{LiCo}_x A_y B_z O_2$  where A denotes at least one element selected from the group consisting of Al, Cr, V, Mn and Fe, and B denotes at least one element selected from the group consisting of Mg and  $\text{Ca}_1$  and x, y and z are such that  $0.9 \le x < 1$ , and  $0.001 \le y < 0.05$ , and  $0.001 \le z < 0.05$ ; and the non aqueous electrolyte comprises a lithium salt dissolved in the electrolyte.
- 3. (Currently Amended) A The non-aqueous electrolyte secondary cell according to claim 2, wherein said the negative electrode uses an active material capable of doping/undoping lithium



ions; said the active material being such an active material including a material selected from the group comprising consisting of a carbonaceous material, an alloy material, and a polymer including polyacetylene polymer.

- 4. (Currently Amended) A The non-aqueous electrolyte secondary cell according to claim 3, wherein said the negative electrode active material, capable of doping/undoping of lithium ion, comprises a carbonaceous material which comprises at least one of a is selected from the group of a pyrocarbons, pitch coke, needle coke, petroleum coke, graphite, vitreous carbon fibers, sintered organic polymer compounds, carbon fiber, and activated charcoal.
- 5. (Currently Amended) A <u>The</u> non-aqueous electrolyte secondary cell according to claim 3, wherein said the negative electrode is a material that can be alloyed with lithium and includes a compound represented by a chemical formula  $M_xM'_yLi_z$  where M is a typical an element of the group <u>3A3B</u> or a metal other than the group <u>4A4B</u> excluding carbon, M' is one or more metal element other than the element Li and the element M, x is a numerical value larger than 0, and y, z are numerical values not less greater than 0.
- 6. (Currently Amended) A The non-aqueous electrolyte secondary cell according to claim 2, wherein said the electrode is a band-shaped positive electrode coated with a positive electrode mixture containing the positive electrode active material on both surfaces of a metal foil; and a band-shaped negative electrode, said positive the negative electrode coated with a negative electrode mixture containing the negative electrode active material on both surfaces of a metal foil and said the negative electrode being stacked and spinally spirally wound by interposing a separator in-between.

- wherein said the electrolyte is a solution of an electrolyte in a non-protonic non-aqueous solvent.
  - 8. (Currently Amended) A <u>The</u> non-aqueous electrolyte secondary cell according to claim 7, wherein said the electrolyte is a solution of a mixture of one or more selected from cyclic carbonates or chained carbonates.

7. (Currently Amended) A The non-aqueous electrolyte secondary cell according to claim 2,

- 9. (Currently Amended) A <u>The</u> non-aqueous electrolyte secondary cell according to claim 7 8 wherein said the electrolyte comprises, as the cyclic carbonate, a solvent selected from the group eonsisting of at least one of an ethylene carbonate, propylene carbonate, butylene carbonate, vinylene carbonate and gamma butyrolactone, said the electrolyte comprising, as the chained carbonate, a solvent selected from the group consisting of dimethyl carbonate, diethyl carbonate, and dipropyl carbonate.
- 10. (Currently Amended) A method for the preparation of a positive electrode active material comprising the steps of:
- (a) mixing a cobalt compound, a lithium compound, a compound of at least one element selected from the group consisting of aluminum, chromium, vanadium, manganese and iron and a compound of at least one element selected from the group consisting of magnesium and calcium, at a pre-set ratio; and
- (b) sintering a mixture from said the mixing step to produce a compound represented by the general formula LiCo<sub>x</sub>A<sub>y</sub>B<sub>z</sub>O<sub>2</sub> where A denotes at least one <u>element</u> selected from the group consisting of Al, Cr, V, Mn and Fe, <u>and</u> B denotes at least one <u>element</u> selected from the group

consisting of Mg and Ca, and x, y and z are such that  $0.9 \le x < 1$ ,  $0.001 \le y \le 0.05$ , and  $0.001 \le z \le 0.05$ ;

said the compound of at least one element selected from the group selected from the group consisting of magnesium and calcium, as used in said the mixing step, being magnesium carbonate or calcium carbonate.

- 11. (Currently Amended) A method for the preparation of a non-aqueous electrolyte secondary cell comprising a positive electrode, a negative electrode, and a non-aqueous electrolyte interposed between said the positive and negative electrodes, comprising, in producing said the positive electrode, the steps of:
- (a) mixing a cobalt compound, a lithium compound, a compound of at least one element selected from the group consisting of aluminum, chromium, vanadium, manganese and iron and a compound of at least one element selected from the group consisting of magnesium and calcium, at a pre-set ratio; and
- (b) sintering a mixture from said the mixing step to produce a compound represented by the general formula  $\text{LiCo}_x A_y B_z O_2$  where A denotes at least one element selected from the group consisting of Al, Cr, V, Mn and Fe, and B denotes at least one element selected from the group consisting of Mg and Ca, and x, y and z are such that  $0.9 \le x < 1$ , and  $0.001 \le y \le 0.05$ , and  $0.001 \le z \le 0.05$ ; and

said the compound of at least one element selected from the group consisting of magnesium and calcium, as used in said the mixing step, being magnesium carbonate or calcium carbonate.



- 12. (Currently Amended) A <u>The</u> method for the preparation of a non-aqueous electrolyte secondary cell according to claim 11, wherein said the negative electrode containing contains an active material capable of doping/undoping lithium ions; said the active material is selected from the group consisting of a comprising a carbonaceous material, and a polymer including polyacetylene polymer.
- 13. (Currently Amended) A <u>The</u> method for the preparation of a non-aqueous electrolyte secondary cell according to claim 12, wherein said the negative electrode, capable of lithium doping/undoping of lithium ion, comprises carbonaceous material which is selected from the group consisting of a pyrocarbon, pitch coke, needle coke, petroleum coke, graphites, vitreous carbon fibers, sintered organic high polymer compounds, carbon fiber, and activated charcoal.
- 14. (Currently Amended) A <u>The</u> method for the preparation of a non-aqueous electrolyte secondary cell according to claim 12, wherein said the negative electrode is a material that can be alloyed with lithium and includes a compound represented by a chemical formula M<sub>x</sub>M'<sub>y</sub>Li<sub>z</sub> where M is a typical an element of the group <u>3A3B</u> or a metal other than the group <u>4A4B</u> excluding carbon, M' is one or more metal element other than the element Li and the element M, x is a numerical value larger than 0, and y, z are numerical values not less greater than 0.
- 15. (Currently Amended) A The method for the preparation of a non-aqueous electrolyte secondary cell according to claim 11 wherein said the electrode is a band-shaped positive electrode coated with a positive electrode mixture containing the positive electrode active material on both surfaces of a metal foil, and a band-shaped negative electrode coated with a

metal foil, said the positive electrode and said the negative electrode being stacked and wound spirally by interposing a separator in-between.

132

- 16. (Currently Amended) A <u>The</u> method for the preparation of a non-aqueous electrolyte secondary cell according to claim 11, wherein said the electrolyte is a solution of an electrolyte in a non-protonic non-aqueous solvent.
- 17. (Currently Amended) A <u>The</u> method for the preparation of a non-aqueous electrolyte secondary cell according to claim 16, wherein said the electrolyte is a solution of a mixture of one or more selected from cyclic carbonates or chained carbonates.
- 18. (Currently Amended) A The method for the preparation of a non-aqueous electrolyte secondary cell according to claim 16, wherein said the electrolyte uses, as the cyclic carbonate, a solvent selected from the group consisting of ethylene carbonate, propylene carbonate, butylene carbonate, vinylene carbonate and gamma butyrolactone, said the electrolyte using, as the chained carbonate, a solvent selected from the group consisting of dimethyl carbonate, diethyl carbonate, and dipropyl carbonate.
- 19. (Currently Amended) A <u>The</u> method for the preparation of a non-aqueous electrolyte secondary cell according to claim 16, wherein said electrolyte comprises one of the inorganic solid electrolyte and a high molecular solid electrolyte as material exhibiting lithium ion conductivity.



20. (Currently Amended) A The method for the preparation of a non-aqueous electrolyte secondary cell according to claim 16 wherein said the electrolyte comprises one or more lithium salts selected from the group consisting of LiCl, LiBr, LiPF<sub>6</sub>, LiClO<sub>4</sub>, LiAsF<sub>6</sub>, LiBF<sub>4</sub>, LiCH<sub>3</sub>SO<sub>3</sub>, LiN(CF<sub>3</sub>SO<sub>2</sub>)<sub>2</sub>, or LiB(C<sub>6</sub>H<sub>5</sub>)<sub>4</sub>.